

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

adds **TROTON** **ML amber** **CAVITY WAX**



PRODUCT DESCRIPTION

One- component product based on wax and impregnates, designed to protect closed profiles of car-body (eg. doors, bonnets, sills) from corrosion . It has good penetrating properties into the gaps and displaces of the surfaces moisture. Creates a flexible, airtight coating that protect against water and salt. It doesn't react with painted surfaces.

PHYSICAL AND CHEMICAL PROPERTIES

- Color: amber
- Capacity : 1 liter
- Density*: 0,85 – 0,89 kg/l
- Viscosity: 20-25 seconds (Ford cup 4 mm.)
- Efficiency: approx. 0,1 kg/m² for 100 µm wet layers
- Temperature resistance: -25 to 80°C

Drying time

- Touch dry*: 90 - 120 min. (± 100 µm)
- Completely dry*: 2 – 3 h. (± 100 µm)

* temp. 20°C, RH 65%

VOC CONTENT

VOC = 402,1 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat..B/5) at the level of 840[g/l] for the ready product.

USAGE

- Surface to be treated must be clean, dry, degreased, free from dust and rust.
- Shake the can well before use.
- Product can be applied on closed profiles by underbody coating gun with air-pressure of 3-6 bar.
- Used equipment can be cleaned with solvents straight after use. After curing product can be removed only mechanically.

Caution: To maintain safety, always follow the instructions given in the Safety Data Sheet for the given product.

STORAGE

Store the product in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight. Best storage temperature : 10 to 30⁰C.

EXPIRY DATE

24 months from production date.

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses.

Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.

TROTON Sp. z o.o.
Ząbrowo, Poland

TROTON Sp. z.o.o

Address: Ząbrowo 14A, 78-120 Gościno, Poland, Tel: +48 94 35 123 94

Tel/Fax: +48 94 35 126 22 Website: www.troton.com.pl Email: troton@troton.com.pl

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

addsTROTON ML CAVITY WAX transparent



PRODUCT DESCRIPTION

One- component product based on wax and impregnates, designed to protect closed profiles of car-body (eg. doors, bonnets, sills) from corrosion . It has good penetrating properties into the gaps and displaces of the surfaces moisture. Creates a flexible, airtight coating that protect against water and salt. It doesn't react with painted surfaces.

PHYSICAL AND CHEMICAL PROPERTIES

- Color: transparent
- Capacity : 1 liter
- Density*: 0,85 – 0,89 kg/l
- Viscosity: 20 seconds (Ford cup 4 mm.)
- Efficiency: approx. 0,2 kg/m² for 100 µm wet layers
- Temperature resistance: -25 to 160°C

Drying time

- Touch dry*: 90 - 120 min. (± 100 µm)
- Completely dry*: 4 – 6 h. (± 100 µm)

* temp. 20°C, RH 65%

VOC CONTENT

VOC = 450,9 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat..B/5) at the level of 840[g/l] for the ready product.

USAGE

- Surface to be treated must be clean, dry, degreased, free from dust and rust.
- Shake the can well before use.
- Product can be applied on closed profiles by underbody coating gun with air-pressure of 3-6 bar.
- Used equipment can be cleaned with solvents straight after use. After curing product can be removed only mechanically.

Caution: To maintain safety, always follow the instructions given in the Safety Data Sheet for the given product.

STORAGE

Store the product in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight. Best storage temperature : 10 to 30°C.

EXPIRY DATE

24 months from production date.

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses.

Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.

TROTON Sp. z o.o.

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

*adds*TROTON SPRAY ML INSIDECOATING



PRODUCT DESCRIPTION

One-component , wax-based product designed to create anticorrosion protect in cavity areas of car-body (eg. Doors, bonnets, sills etc.). Product has very good penetrating properties and is water-repellent. After drying creates elastic, tight protective coating resistant to harmful effect of weather condition, water, salt and weak acids.

It doesn't react with painted surfaces.

PHYSICAL AND CHEMICAL PROPERTIES

Color: amber, transparent
Glass grade: mat
Volume: 400 ml

VOLITARE AND CHEMICAL PROPERTIES

VOC for mixture= 574 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat..B/5) at the level of 840[g/l] for the ready product.

USAGE

- Best processing temperature 15 – 25⁰C. Aerosol should have room temperature.
- Shake before using for 2 minutes and try it on cardboard.
- Apply the wax coating in several layers.
- Don't spray on the exhaust, brake systems or on motor parts.
- Remove excess material with mineral spirits.
- **After use clean aerosol's outlets** – hold down aerosol's valve, push the bottom and release contents for 5 seconds.

Caution: To maintain safety, always follow the instructions given in the Safety Data Sheet for the given product.

STORAGE

Store the product in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight.

EXPIRY DATE

5 years from production date, provided the storage condition.

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses.

Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.

TROTON Sp. z o.o.
Ząbrowo, Poland