

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

addsTROTON INTERGUM UNDERBODY COATING



PRODUCT DESCRIPTION

Fast-drying agent based on bitumen, designed for the permanent protection of the car underbody against rust. After drying product creates tightly adherent coating, giving good mechanical protection in different climatic conditions. It is characterized by excellent soundproofing properties. Can't be coated by any kind of lacquer systems.

PHYSICAL AND CHEMICAL PROPERTIES

- Color: black
- Viscosity*: 100 – 200 Pas
- Density: 1,03 – 1,06 kg/l
- Capacity: 1 liter
- Efficiency: approx. 0,6kg/m² for 600 µm wet layer
- Temperature resistance: -25 to 80⁰C
- Dry to touch *: 120 -180 min. for 600 µm wet layer
- Completely dry*: 4 – 6 h. for 600 µm wet layer
- Removal: fresh coat - solvent
cured coat – mechanically

*= at 20⁰C, 65% RH

VOC CONTENT

VOC= 378,2 g/l

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat..B/5) at the level of 840[g/l] for the ready product.

USAGE

- Surface to be treated must be clean, dry, degreased, free from dust and rust.
- Shake the can well before use.
- Product can be applied by underbody coating gun with air-pressure of 3-6 bar.
- The best spraying distance is approx. 30 cm.
- If thicker layers is recommended, first layer must be dry before apply another coat.
- Used equipment can be cleaned with solvents straight after use.

Caution: To maintain safety, always follow the instructions given in the Safety Data Sheet for the given product.

STORAGE

Store the product in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight. Best storage temperature : 10 to 30°C.

EXPIRY DATE

24 months from production date.

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses.

Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.

TROTON Sp. z o.o.
Ząbrowo, Poland

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

addsTROTON SPRAY INTERGUM UNDERBODY COATING



PRODUCT DESCRIPTION

Fast-drying agent based on bitumen and waxes designed for the permanent protection of the car underbody against rust. After drying product leaves tightly adherent coating, giving good mechanical protection in different climatic conditions. It is characterized by excellent soundproofing properties . Can't be coated by any kind of lacquer systems.

PHYSICAL AND CHEMICAL PROPERTIES

- Colour: black
- Glass grade: mat
- Volume: 500 ml
- Dust dry*: after 60 minutes (in room temperature)

VOC CONTAINS

VOC for mixture= 545,3 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat..B/5) at the level of 840[g/l] for the ready product.

*drying time depends on the temperature, humidity and thickness of the coating.

USAGE

- The surface to be treated should be clean, dry and free of grease.
- Best processing temperature 15 – 25⁰C. Aerosol should have room temperature.
- Shake before using for 2 minutes and try it on cardboard.
- During lacquering hold aerosol in 25÷30 cm distance from the surface.
- **Clean the spray nozzle after use!** – Holding the can with the valve pointing downward, press the button emptying the content for about 5 seconds.

Caution: For safety reasons always comply with information provided in the Material Safety Data Sheet.

STORAGE

Store the product components in sealed container, in dry and cool places, away from heat sources, as well as direct sunlight.

EXPIRY DATE

5 years from the production date.

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses. Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.

TROTON Sp. z o.o.
Ząbrowo, Poland

TECHNICAL INFORMATION
FOR PROFESSIONAL USE ONLY**addsTROTON**
INTERGUM
UNDERBODY COATING
brushable**PRODUCT DESCRIPTION**

Fast-drying agent based on bitumen, designed for the permanent protection of the car underbody against rust. After drying product creates tightly adherent coating, giving good mechanical protection in different climatic conditions. It is characterized by excellent soundproofing properties. Can't be coated by any kind of lacquer systems.

PHYSICAL AND CHEMICAL PROPERTIES

- Color: black
- Viscosity*: 1040 – 2000 mPas
- Density*: 1,26 – 1,30 kg/l
- Capacity: 1 kg
- Efficiency: approx. 0,7 kg/m² for 500 µm wet layer
- Temperature resistance: -25 to 80°C
- Dry to touch*: 90 - 120 min. for 500 µm wet layer
- Completely dry*: 10 – 12 h. for 500 µm wet layer
- Removal: fresh coat - solvent
cured coat - mechanically

*at ±20°C, 65% RH

VOC CONTENT

VOC = 325,9 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat..B/5) at the level of 840[g/l] for the ready product.

USAGE

- Surface to be treated must be clean, dry, degreased, free from dust and rust.
- Shake the can well before use.
- Product can be applied by brush or spatula.
- If thicker layers is recommended, first layer must be dry before apply another coat.

Caution: To maintain safety, always follow the instructions given in the Safety Data Sheet for the given product.

STORAGE

Store the product in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight. Best storage temperature : 10 to 30⁰C.

EXPIRY DATE

24 months from production date.

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses.

Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.

TROTON Sp. z o.o.
Ząbrowo, Poland